

## **DREAM VELVET**











Skład | Composition

Gramatura | Weight

Szerokość | Width

Rodzaj | Type

Grupa asortymentowa | Brand

100% PES

 $360 \text{ g/m}^2 \pm 5\%$ 

142 ± 3 cm

dzianina | knitted fabric

tkaniny obiciowe | upholstery fabric

AM.	Odporność na ścieranie   Abrasion resistance PN-EN ISO 12947-2:2017-02	90 000 suwów/rubs	В
	Mechacenie i pilling   Fuzzing and pilling PN-EN ISO 12945-2:2002	5	А
<b>%</b>	Przesunięcie w szwie   Seam slippage PN-EN ISO 13936-2:2005	2   osnowa   warp 2   wątek   weft	А
	Tarcie mokre   Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	А
	Tarcie suche   Dry rubbing PN-EN ISO 105-X12:2016-08	5	А
2	Test papierosa   Cigarette test PN-EN 1021-1:2014-12		✓

- 1. The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Sp. z o.o. is not liable for mechanical damage and such as may be attributa-ble to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.



Konserwacja Maintenance













