





# BONITA

209.01-209.20

 Non-flammable  
atest papierosa



Skład   Composition	100% PES
Gramatura   Weight	370 g/m <sup>2</sup> ± 5%
Szerokość   Width	142 ± 3 cm
Rodzaj   Type	tkanina   woven fabric
Grupa asortymentowa   Brand	tkaniny obiciowe   upholstery fabric

	Odporność na ścieranie   Abrasion resistance PN-EN ISO 12947-2:2017-02	60 000 suwów/rubs	A
	Mechacenie i pilling   Fuzzing and pilling PN-EN ISO 12945-2:2002	5	A
	Tarcie mokre   Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	A
	Tarcie suche   Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	A
	Test papierosa   Cigarette test PN-EN 1021-1:2014-12		✓

## Konserwacja Maintenance



1. The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
3. Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
5. Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
6. Long-term exposure to sunlight can cause discolouration.
7. According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.