UTTARIO VELVET







Konserwacja Maintenance

40°

2951-2980

Skład | Composition

Gramatura | Weight

Szerokość | Width

Rodzaj | Type

Grupa asortymentowa | Brand

100% PES

260 g/m²

142 ± 3 cm

dzianina | knitted fabric

tkaniny obiciowe | upholstery fabric

M.	Odporność na ścieranie Abrasion resistance PN-EN ISO 12947-2:2017-02	45 000 suwów/rubs	A
	Mechacenie i pilling Fuzzing and pilling PN-EN ISO 12945-2:2002	4-5	A
%	Przesunięcie w szwie Seam slippage PN-EN ISO 13936-2:2005	3 osnowa warp 3 wątek weft	A
	Tarcie mokre Wet rubbing PN-EN ISO 105-X12:2016-08	4-5	A
	Tarcie suche Dry rubbing PN-EN ISO 105-X12:2016-08	4-5	A
2	Test papierosa Cigarette test PN-EN 1021-1:2014-12		

1.	The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning
	of the fabric but the process does not affect the look

- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Sp. z o.o. is not liable for mechanical damage and such as may be attributa-ble to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- 5. Due to friction against the fabric, colourants can migrate from darker to brighter
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.

