

# SL 430

 2161-2191



WATER  
REPELLENT



PETPROOF



NON-FLAMMABLE



Skład | Composition

100% PES

Gramatura | Weight

310 g/m<sup>2</sup> ± 5%

Szerokość | Width

142 ± 3 cm

Rodzaj | Type

dzianina | knitted fabric

Grupa asortymentowa | Brand

tkaniny obciowe | upholstery fabric



Odporność na ścieranie | Abrasion resistance  
PN-EN ISO 12947-2:2017-02

40 000 suwów/rubs

B



Mechacenie i pilling | Fuzzing and pilling  
PN-EN ISO 12945-2:2002

5

A



Przesunięcie w szwie | Seam slippage  
PN-EN ISO 13936-2:2005

3 | osnowa | warp  
3 | wątek | weft

A



Tarcie mokre | Wet rubbing  
PN-EN ISO 105-X12:2016-08

4

A



Tarcie suche | Dry rubbing  
PN-EN ISO 105-X12:2016-08

3

C



Test papierosa | Cigarette test  
PN-EN 1021-1:2014-12

✓

Konserwacja  
Maintenance



- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.