

## CORD











205.01-205.21

Skład | Composition

Gramatura | Weight

Szerokość | Width

Rodzaj | Type

Grupa asortymentowa | Brand

100% PES

 $320 \text{ g/m}^2 \pm 5\%$ 

142 ± 3 cm

dzianina | knitted fabric

tkaniny obiciowe | upholstery fabric

M.	Odporność na ścieranie   Abrasion resistance PN-EN ISO 12947-2:2017-02	45 000 suwów/rubs	А
	Mechacenie i pilling   Fuzzing and pilling PN-EN ISO 12945-2:2002	5	А
×	Przesunięcie w szwie   Seam slippage PN-EN ISO 13936-2:2005	4   osnowa   warp 4   wątek   weft	В
	Tarcie mokre   Wet rubbing PN-EN ISO 105-X12:2016-08	5	А
	Tarcie suche   Dry rubbing PN-EN ISO 105-X12:2016-08	5	А

Konserwacja















- The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning
  of the fabric, but the process does not affect the look.
- Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- 3. Sp. z o.o. is not liable for mechanical damage and such as may be attributa-ble to the improper use and/or cleaning of the fabric.
- 4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.

Test papierosa | Cigarette test

PN-EN 1021-1:2014-12

- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.

