## **CASABLANCA**











Skład | Composition
Gramatura | Weight
Szerokość | Width
Rodzaj | Type
Grupa asortymentowa | Brand

100% PES 310 g/m<sup>2</sup> ± 5%

142 ± 3 cm

dzianina | knitted fabric

tkaniny obiciowe | upholstery fabric

M.	Odporność na ścieranie   Abrasion resistance PN-EN ISO 12947-2:2017-02	45 000 suwów/rubs	А
×	Przesunięcie w szwie   Seam slippage PN-EN ISO 13936-2:2005	1   osnowa   warp 5   wątek   weft	А
	Test papierosa   Cigarette test PN-EN 1021-1:2014-12		✓

Konserwacja Maintenance















- 1. The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
- 2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
- 3. Sp. z o.o. is not liable for mechanical damage and such as may be attributa-ble to the improper use and/or cleaning of the fabric.
- Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
- 5. Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
- 6. Long-term exposure to sunlight can cause discolouration.
- According to ISO 13936, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
- It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.

