

TECHNICAL DATA SHEET – FINESSE WR			
TEST TYPE	UNIT	RESULT	TEST METHOD
WEIGHT	gr/m2	330±20	ISO 30801
WIDTH	cm	142±2	ISO 3932-76
TENSILE STRENGTH (Warp – Length)	N	740	ISO 13934-2:2014 Grab method
TENSILE STRENGTH (Weft – Width)	N	770	ISO 13934-2:2014 Grab method
ABRASION RESISTANCE	12kPa	+30000	ISO 12947-2: 1998
PILLING RESISTANCE	@5000 revs	4	ISO 12945-2: 2000
COLOUR FASTNESS TO RUBBING (DRY & WET)	1-4	4	ISO 105-X12
DIMENSIONAL STABILITY TO DRY CLEANING	1 dry cleaning	Lenghtwise: -1.1%; Widthwise: -0.2%	ISO 3759:2011
DIMENSIONAL STABILITY TO WASHING	1 wash	Lenghtwise: -1.3%; Widthwise: -0.6%	ISO 3759:2011
COLOUR FASTNESS TO LIGHT	Grade (BWS)	4	ISO 105-B02:2014; Method2
SEAM SLIPPAGE	mm	2.8	ISO 13936-2:2004
COMPOSITION & FINISHES		WASHING INSTRUCTIONS	
100% Polyester		Washing at 30 oC. Use neutral derergents.	
Type of Finish: WR (water-repellent)		Iron on reverse (up to 115 oC)	
		Hand or machine washing, do not spin. Avoid sun exposure.	
<i>Date: 05.06.2023</i>		Do not bleach	