

CIRO

Product characteristics

Applications	UPHOLSTERY
Composition	100% Polyester
Statistic Code	55121990
Dyeing method	Piece dyed
Available colours	19
Minimum workable width	140 CM
Roll length	40 M
GSM	410 GS/M
Backing/Finishing	Fleece Back. Water Proof

Durability specifications

Test	Test Specification	Unit	Testresult	
			WARP	WEFT
Colour Fastness To Rubbing	ISO 105-C06	grade	4-5	4-5
Colour Fastness To Light	UNE 40187/ BS 1006-B02	grade	4-5	4-5
Pilling	EN ISO/DIS 12945-1	grade	4-5	4-5
Abrasion Resistance	EN ISO 12947-2:1998	Martindale	90.000 Cycles	

Processing specifications

Test	Test Specification	Unit	Testresult	
			WARP	WEFT
Breaking Strength	ISO 13937-3	Newton	940	582
Tearing Strength	BS 3320:1998 y BS 2543:1995	mm	2.9	2.1

Cleaning specifications and Instructions

Test	Test Specification	Unit	Testresult	
			WARP	WEFT

Instructions



Colors

