

# SL 410

 2911-2941



**Skład | Composition**

100% PES

**Gramatura | Weight**

450 g/m<sup>2</sup> ± 5%

**Szerokość | Width**

142 ± 3 cm

**Rodzaj | Type**

dzianina | knitted fabric

**Grupa asortymentowa | Brand**

tkaniny obiciowe | upholstery fabric

 **Odporność na ścieranie | Abrasion resistance**  
PN-EN ISO 12945-2:2015-02

90 000 suwów/rubs

A

Konserwacja  
Maintenance

 **Mechanizm i pilling | Fuzzing and pilling**  
PN-EN ISO 12945-2:2002

4-5

A



 **Przesunięcie w szwie | Seam slippage**  
PN-EN ISO 13935-2:2005

2 | osnowa | warp  
2 | wątek | weft

A



 **Test papierosa | Cigarette test**  
PN-EN1021-1:2014-12

✓



1. The level of Cleanaboo and Cleanaboo+ protection can decrease after each cleaning of the fabric, but the process does not affect the look.
2. Respective fabric batches may differ slightly in shade from the colours presented in the sampler.
3. Sp. z o.o. is not liable for mechanical damage and such as may be attributable to the improper use and/or cleaning of the fabric.
4. Bobbling and pilling are caused by the properties of the fabric and impossible to avoid entirely. This is a natural process, which occurs as the fabric is used.
5. Due to friction against the fabric, colourants can migrate from darker to brighter fabrics.
6. Long-term exposure to sunlight can cause discolouration.
7. According to ISO13935, the proper thickness of the bead is 33-35 of the stitching per 10 cm of the fabric with the minimum distance of the stitching from the edge of the fabric of at least 1.5 cm.
8. It is assumed that depending on the type of fabric, resistance to abrasion within the scope of 2,000-4,000 Martindale cycles corresponds with the period of 1 year of the proper use of the fabric.