

SL 185

			category
	Abrasion test (cycles) EN ISO 12947-1,2	>15.000 (loss of chenille)	65.000 (Martindale)
	Pilling test EN ISO 12945-2 (2.000 T)	4	B
	Tensile strength EN ISO 13934-1 warp: weft:	2470 N 1530 N	A A
	Tear growth resistance EN ISO 13937-3 warp: weft:	487 N 229 N	A A
	Resistance seam slippage EN ISO 13936-2 warp: weft:	3.0 mm 3.0 mm	A A
	Fastness to rubbing dry EN ISO 105- X12 bright colors dark colors	4- 5 4- 5	A A
	Fastness to rubbing wet EN ISO 105- X12 bright colors: dark colors:	4- 5 4- 5	A A
	Fastness to light EN ISO 105-B02- 2 bright colors: dark colors:	6 6	A A
Permissible color tolerance DIN EN 20105-A02		min. grade 4	passed

Rotational strength: 245 m	Width: 142 cm + - 2 cm	145 cm + - 2 cm
Thickness: 1.5 mm + - 2 %	Weight m DIN EN 12127: 880 g + - 5 %	Weight m ² DIN EN 12127: 620 g + - 5 %

Composition:

	Surface EU 1007 2011:	100% polyester
---	-----------------------	----------------

	Base EU 1007 2011:	-
---	--------------------	---

Recommended care labeling:

	washing		bleaching		drying		ironing		dry cleaning
---	---------	---	-----------	---	--------	---	---------	---	--------------

Typical product characteristics:

Pigment bleed and color abrasion may occur with dark and intensive colors. Pilling cannot be avoided and may also occur through the adhesion of fibers from other sources. All flat-woven fabrics may roughen in use and patina and glossy spots may occur. Pulled threads are to be expected if sharp objects catch in the fabric. Depending on the material, a slight striped effect may occur. In the case of chenille fabrics a change in the run nap (shading), shimmer (color change depending on the light angle) and the fattening out of the chenille effect are inevitable. Over the course of time, a certain amount of color fading can be expected. This is due to light incidence or abrasion caused by heavy usage of chenille fabrics. Minor variations in color and texture between product lots are unavoidable and may occur. Dark and intense colors tend to abrasion.

I

ValDouro
TEXTILES | EST 1997