

CORAL

INDOOR FABRIC

Nombre del artículo

Article name

Nom de l'article

INFORMACIÓN GENERAL

General information / Informations générales

Composición Composition	%	32%PES, 29%VIS, 13%LIN, 26%CO
Ancho Width Largueur	cm	140
Masa superficial Weight Masse	g/m ²	426±5

ENSAYOS DE LABORATORIO

Tests results / Test de laboratoire

Resistencia de costuras Seam strength Résistance de la couture	mm	3,8 (Urdimbre/Warp/Chaîne) – 3,0 (Trama/Weft/Trame)	
Resistencia a la abrasión Abrasion resistance Résistance à l'abrasion	Nº ciclos No. Cycles Non Cycles	40.000	
Resistencia al pilling Pilling resistance Pilling résistance	Grado Degree Degré	3-4	
Solidez al frote Rubbing fastness Solidité au frottement		Seco/Dry/Sécher	Húmedo/Wet/Humide
	Solidez/fastness/solidité	5	5
	Descarga/Discharge/Décharger	5	5

SÍMBOLOS DE CONSERVACIÓN

Care instructions / Instructions d'entretien

