

Lintex

OUTDOOR FABRIC

Weight	230 ± 10 gr/m ²	ISO 3801
Width	155 ± 5 cm	ISO 22198
Seam Slippage	Warp: 2/3 mm; Weft: 2/3 mm	EN ISO 13936-2
Tear Strength	Warp: > 110 N; Weft: > 120 N	EN ISO 13937-2
Tensile Strength	Warp: > 1800 N; Weft: > 1200 N	EN ISO 13934-1
Water Repellency	Pass	AATCC 22:2014
Color Fastness to Rubbing	4-5	EN ISO 105-X12
Color Fastness to Light	7-8	EN ISO 105-B04
Color Fastness to Pool Water	4-5	EN ISO 105-E03
Color Fastness to Sea Water	4-5	EN ISO 105-E02
Color Fastness to Water	4-5	EN ISO 105-E01
Color Fastness to Dry Cleaning	4-5	EN ISO 105-D01:2010
Pilling	4-5	EN ISO 12945-2
Flammability	Pass	EN ISO 1021-1
Accelerated Weathering QUV 1500 hours ASTM G 154:	50% Tenacity	EN ISO 105 B04
Accelerated Weathering QUV 1500 hours ASTM G 154	50% Elongation	ASTM G 154 (1200 HOURS)

Lintex

OUTDOOR FABRIC

OEKO-TEX: Conform

Composition: 100% Olefin

Treatments: W/R + PU Membrane

Dimensional Change in Washing & Drying: Warp: < 0.5% Weft: < 0.5% EN ISO 5077:2007, EN ISO 3759:2007

Martindale Abrasion: > 20 000 12KPA – EN ISO 12947-2

Spray Test: 4-4 – EN ISO 4920

Anti Bacterial: Reduction 99% Effective – JIS L 1902

WASHING INSTRUCTIONS

Iron on the face (up to 50°C).

No dry cleaning, no tumbling, do not bleach.

Washing at 30°C, use neutral detergents.

Do not use optical bleaching.

Hand or machine washing, do not spin.

Don't leave your product under direct sunlight if the outside temperature exceeds 30°C.

