

LINUS

TEST TYPE	UNIT	RESULT	TEST METHOD
WEIGHT	gr/m2	360±10	ISO-DIS 30801
THICKNESS	mm	1.5±0.05	ISO 2589
WIDTH	cm	142±1	ISO-3932-76
TENSILE STRENGTH(Warp)	N	702 N	ISO EN 13934-1: 1999
TENSILE STRENGTH(Weft)	N	328 N	ISO EN 13934-1: 1999
TEAR STRENGTH (Warp)	N	101 N	TS EN ISO 13938-3:2002
TEAR STRENGTH (Weft)	N	59 N	TS EN ISO 13938-3:2002
PILLING @ 2000 cycles		4	ISO 12945-1:2001
TYPE OF FINISH		Water Repellent	
ABRASION RESISTANCE	CYCLE / TOUR	+30000	ISO 12947-2:2016
COLOUR FASTNESS TO LIGHT	Grade	5	DIN ISO EN 105-B02
COLOUR FASTNESS TO RUBBING (DRY & WET)	Grade	Dry: 4; Wet: 4-5	DIN ISO EN 105-X12
WASHING SHRINKAGE AT 40oC	%	Warp 1.2%, Weft 1.3%	ISO-675-1979
SEAM SLIPPAGE	mm	Warp: 3.2; Weft: 3.2	BS 2543-1995

Chemical Composition		Washing Instructions
Polyester	80%	Iron on reverse (up to 115 oC)
Viscose	20%	Use only perchlorethylene and avoid mechanical abrasion
Construction	Bonded Woven Fabric	Do not bleach
AZO dyestuff	NOT DETECTED	Washing at 30 oC. Use neutral derergents. Do not use optical bleaching
		Hand or machine washing, do not spin. Avoid sun exposure.